



## KEIM CONTACT PLUS

---

### 1. Product Information

Keim Contact Plus is a silicate based priming coat for renovation work. Keim Contact Plus contains pure acrylate, glass fibres and silicate minerals in balanced grain sizes and shapes.

### 2. Field Of Application

Keim Contact Plus is used to treat old synthetic resin bound or oil based coats in preparation for top coats of Keim dispersion silicate paint according to DIN 18 363, Section 2.4.1. A silicate based priming coat for surface equalisation and renovation especially on previously painted surfaces.

### 3. Product Characteristics

#### **Material Data:**

- Specific Weight 1.74 g/cm<sup>3</sup>
- Resistance to vapour diffusion sd=0.02m
- Colour white

### 4. Application

#### **Substrate Preparation:**

All loose and flaking paint must be thoroughly removed using wire brushes and broad bladed scrapers to get back to a sound edge; these edges should then be feathered in. Any gloss or shiny surfaces should be thoroughly flatted down using sand or emery paper to create a good key.

When all surfaces are clean, sound, wind dry, dust free and free from all surface contaminants, decoration using Keim Mineral Paints may proceed.

#### **Processing:**

Dilute Keim Contact Plus with Keim Dilution 1 lt per 10 kg. Apply uniformly with brush or roller.

#### **Subsequent Coats:**

Keim Contact Plus must be overcoated with one or two coats of Keim Granital, Keim Royalan or Keim Concretal. With light colours (price group I) apply only one opaque finishing coat undiluted. Darker colours (price groups II, III and IV) require two subsequent coats.

#### **Temperature:**

Keim Contact Plus should only be applied at ambient and substrate temperatures exceeding 5°C. It is imperative to protect the façade during the application from rain and sun.

#### **Consumption:**

Approximately 0.5 kg Keim Contact Plus per m<sup>2</sup> on a smooth surface. The consumption rate is intended for guideline purposes only. Exact consumption rates have to be evaluated by site trials.

Consumption rates are offered for guideline purposes only and are quoted for smooth rendered surfaces. Actual rates are the responsibility of the applicator. Project specifications should be referred to for specific rates.

#### **Tools:**

Keim Contact Plus should be applied by brush or roller. After use immediately clean tools in water.

#### **Drying Periods:**

Allow at least 12 hours drying time between individual coats.

---

---

## 5. Packing

5 and 25 kg drums

## 6. Storage

Store cool and frost-free in tightly closed containers.  
Shelf life is 12 months.

## 7. Identification ref. Ordinance of dangerous material.

Not applicable

## 8. Danger class in goodstraffic

Not applicable

## 9. Product Code

Not applicable

## 10. Safety Instructions

Cover surfaces which are not to be painted, in particular glass, natural stone, ceramic etc. Protect eyes and skin against splashes. Keep out of reach of children.

Observe the actual general rules of building technology. Subject to changes in the interest of product and application improvements. This edition replaces former editions.



**KEIM**  
MINERAL PAINTS LTD

Santok Building  
Deer Park Way, Donnington Wood  
Telford, Shropshire TF2 7NA  
Tel. (01952) 231250  
Fax. (01952) 231251