



## **M20 PLASTERED/RENDERED/ROUGHCAST COATINGS**

### **110 RENDER:**

#### **KEIM UNIVERSAL RENDER & KEIM BRILLANT-PUTZ**

Keim Universal Render is a hydrated lime based renovation and thin layer exterior wall render with fibre reinforcement. It is for use on all mineral substrates, both exterior and interior and has excellent flexibility and high moisture vapour permeability. Keim Brillant-Putz is a lightweight finishing render, available in a variety of textures and colour shades.

**Manufacturer:** Keim Mineral Paints Limited, Santok Building, Deer Park Way, Telford, Shropshire TF2 7NA T: 01952 231250 F: 01952 231251 E: [sales@keimpaints.co.uk](mailto:sales@keimpaints.co.uk)

#### **REFERENCE: KEIM UNIVERSAL RENDER & KEIM BRILLANT-PUTZ**

#### **Preparation:**

Any loose, flaking and unstable material must be identified and then thoroughly removed using stiff brushes and broad bladed scrapers to get back to a sound edge; these edges should then be feathered in. Ensure that any paint materials left remaining and the underlying substrate is sound and adhering well. Any gloss or shiny surfaces should be thoroughly flatted down using sand or emery paper to create a good key.

#### **Keim Algicide**

A non-acid fungicide wash.

Any algae growth should be wire brushed to remove all growths and treated with Keim Algicide, brush applied undiluted and allowed to remain undisturbed for some 3 hours before thoroughly washing off.

When all surfaces are clean, sound, dry, dust free and free from all surface contaminants, application of Keim Universal Render may proceed.

#### **Application:**

##### **Keim Universal Render**

Mixing: Mix in the ratio of 1 kg Keim Universal Render to 0.24 litres water (approximately 6 litres per 25kg bag).

##### **Keim Brillant-Putz**

Mixing: Start with approximately 5.8 litres water to 25 kg and increase if necessary until the render has a creamy consistence, but maximum 8.5lt/25kg. Pour the corresponding water into a suitable container, add Keim Brillantputz and stir in homogenously. Stir well for a few minutes. The mixed mortar should have a creamy consistence.

Materials should be mixed using a mechanical stirrer or plaster mixing machine/sprayer, e.g. Putzmeister or similar.

Apply to pre-wetted surfaces in layers from 4mm minimum to 10mm maximum. Use Keim Universal Render for base coats and Keim Brillant-Putz for the final finishing coat. For subsequent applications do not scratch up applied coat and leave for a minimum period of 12 hours before reapplication. The final layer should be no thicker than 4mm. Finish off using a stainless steel trowel down to grain size and spread over.



Keim Glassfibre Reinforcing Mesh may be incorporated if so required by pressing into newly applied first layer of Keim Universal Render and then applying a further finishing coat.

### **Typical Specification (12mm):**

We advise to apply to pre-wetted surfaces an initial layer of Keim Universal Render of 9mm thickness with Keim Glassfibre Reinforcing Mesh incorporated by pressing into newly applied Keim Universal Render. After a minimum period of 12 hours a finishing layer of Keim Brillant-Putz of 3mm thickness should be applied. The overall thickness should be approximately 12mm. Do not scratch the base coat and finish using with a stainless steel trowel down to grain size and spread over. Work always with the wet-in-wet technique to avoid edges. Use always the same batch number per surface.

### **Finishing:**

All newly rendered areas must be allowed to dry out for a minimum period of 15 days. We would then recommend the render is painted using Keim Mineral Paints. It is possible to apply a single coat of Keim Soldalit in the same colour onto Keim Brillant-Putz in the chosen colour.

## **IMPORTANT INFORMATION REGARDING STANDARD KEIM SPECIFICATIONS**

We have taken every care to ensure that specifications are accurate, if there is any doubt about how to deal with a specific problem or the most suitable products to use, please contact us.

Specifications downloaded from the Keim Mineral Paints website are standard specifications to cover general circumstances and may not be suitable for every situation. Dedicated project specific specifications and product advice can be obtained by contacting [sales@keimpaints.co.uk](mailto:sales@keimpaints.co.uk) or 01952 231250.

It is essential that each stage of the specification is complied with, including level of preparation and drying times between coats, to ensure the best performance from the system applied. All products should be applied in accordance with the specification and relevant datasheets.

General points to be borne in mind when using Keim Mineral Paints are:-

In order for Keim Mineral paint to achieve its permanent bond with the surface it is essential that the following recommendations are followed.

### **Pre-treatment –**

- all areas to be decorated should be free from all surface contaminants, sound, dry and dust free
- all loose, flaking and unstable material must be identified and then thoroughly removed using stiff brushes and broad bladed scrapers to get back to a sound edge; these edges should then be feathered in
- ensure that any paint materials left remaining and the underlying substrate is sound and adhering well
- caution should be taken with the removal of any pre 1960's coatings as they may contain lead
- any gloss or shiny surfaces should be thoroughly flatted down using sand or emery paper to create a good key
- if the surfaces are being chemically stripped ensure that they are thoroughly washed down of all residue prior to decoration. Due to the potential for an osmotic drawing reaction, which can bring contaminants



to the surface, we do not recommend the use of poultice based strippers if the surfaces are to be redecorated

- any powdery or chalking surfaces will require treatment prior to decoration – contact Keim to ascertain the appropriate product
- use only Keim recommended fillers and sealers. Acrylic, resin and gypsum based fillers particularly are not recommended for use with mineral paints

### Material Application –

- always maintain a wet edge and work materials out well
- all materials must be thoroughly mixed beforehand, and periodically during decoration, using a mechanical mixer. We do not recommend intermixing packs, however if this is necessary ensure that products are thoroughly mixed beforehand to ensure even pigment dispersion, prior to mixing
- materials **must not** be applied at temperatures below 5°C nor those in excess of 30°C
- materials **must not** be applied if it is raining or if there is an immediate likelihood of rain
- Keim Mineral Paints should be applied onto wind dry surfaces where the moisture content on or near the surface (to a depth of 5mm approximately) should be no greater than 18% by volume. For on-site purposes a moisture meter may be used to give a qualitative reading – if the reading is in the green zone decoration may proceed
- on newly rendered surfaces we would suggest that a period of at least 15 days (30 days for lime render) is allowed following rendering, prior to the application of Keim paints
- mineral paints are manufactured using natural components and as such can appear to dry out unevenly. This is the way in which they dry, once fully dried any unevenness will disappear. Do not over-roll or touch up the paint during the drying process as this may inadvertently create patching once dry
- mineral paints will lighten as they dry, with a corresponding increase in opacity
- if airless spraying, please contact Keim for details of the appropriate nozzle sizes and optimum mesh and filter types

### **Housekeeping** –

- all adjoining surfaces must be protected during decoration, any splashes/unwanted paint removed immediately, before it is able to completely dry and bond to the surface
- any splashes or spillage should be removed immediately using water - particular note needs to be taken of this in respect of Keim on glass, as it has a slight etching effect if allowed to dry hard
- clean all brushes and tools immediately in water (some ancillary products containing solvents may require white spirit or turpentine, if in doubt please consult the relevant product technical data sheet)
- always store materials upright and secure. Protect from extremes of temperature and store in frost-free conditions

### **General** –

- when ordering reference to the project should be made, to ensure that in the event of re-ordering a colour match can be supplied
- to avoid confusion, the recommendations within this specification should be followed where there are any minor differences between this document and the standard advice on packaging and technical data sheets
- Keim Mineral Paints Ltd operates a policy of 'sale and no return' on all goods supplied in good faith